

Trade name: **SIMONA® PVC Type I**

Revision: 01.10.2014

Date of printing: 18.10.2016

**SIMONA® PVC Type I**

Data sheet update	01.10.2014
Classification	Class 12564
Classification Standard	ASTM D1784-11
Density, g/cc , D-792	1.410
Tensile Strength at yield, psi , D-638	9,000
Tensile Modulus, psi , D-638	486,000
Izod Impact (notched), ft.lbs./in. , D-256	0.8
Shore Hardness, (1 s), ISO 868	84
Coefficient of Thermal Expansion, in./in./°C , D-696	0.8 x 10 <sup>-4</sup>
Heat Deflection Temperature at 264 psi, °F	154
Crystalline melting range, °F , DSC (10 °C/min)	not applicable
Temperature Range, °F	32 to +140
FDA regulations 21 Chapter 1, part 177.2510 for contact with food stuffs	no
Flammability D 635	self-extinguishing
Flammability UL 94	94V-0, 94-5V

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at [mail@simona-america.com](mailto:mail@simona-america.com).